

Abstract Submitted
for the MAR06 Meeting of
The American Physical Society

A study of magnetic domain formation and motion in perpendicularly magnetized ultrathin film using the magnetic ac-susceptibility

NIDAL ABU-LIBDEH, DAVID VENUS, McMaster University — The Complex, low-frequency ac magnetic susceptibility χ has been used to study magnetic domain formation and motion in perpendicularly magnetized ultrathin Fe films on a 2ML Ni/W(110) substrate. Analysis of the real and imaginary part of χ reveals that below a characteristic temperature T_{sat} , the stripe-domain density cannot change quickly enough to maintain equilibrium. This is due to the fact that domain wall creation and/or annihilation is itself an activated process, with nucleation energy E_n , distinct from the pinning of existing domain walls by defects in film structure, with activation energy E_a . T_{sat} , is set by the time scale of the measurements, which is determined by the rate of change of temperature (R). The Magnetic susceptibility was recorded as a function of temperature at different heating rates between 0.03 (K/s) to 1 (K/s). Our results show that below heating rate R_c ($= 0.2$ K/s for 1.5ML Fe film) the susceptibility peak temperature (T_{peak}) decreases as $dT/dR = -200.0$ (s). Above R_c , the susceptibility peak temperature increases as $dT/dR = 16.6$ (s). Preliminary model calculation show the movement of T_{peak} is due to the change in T_{sat} as the heating rate changes. R_c is set by the relative values of E_n and E_a .

Nidal Abu-Libdeh
McMaster University

Date submitted: 30 Nov 2005

Electronic form version 1.4