

Abstract Submitted  
for the MAR07 Meeting of  
The American Physical Society

**Low self-affine exponents of fractured glass ceramics surfaces**

LAURENT PONSON, Federal University of Rio de Janeiro, HAROLD AURADOU, FAST-Universite Paris-Sud, DANIEL BONAMY, ELISABETH BOUCHAUD, SPCSI-Commissariat à l’Energie Atomique, JEAN-PIERRE HULIN, FAST- Universite Paris-Sud, FRACTURE GROUP TEAM, MELANGE ET MILIEUX DISPERSES TEAM — The morphology of fracture surfaces encodes the various complex damage and fracture processes occurring at the microstructure scale during crack propagation. It is now well established that fracture surfaces are self-affine characterized by a roughness exponent usually found close to  $\zeta \approx 0.75$  for a wide range of materials. Recently, fracture surfaces of sandstone were found to be also self-affine but with a lower roughness exponent  $\zeta \approx 0.4-0.5$ . To investigate its origin, we studied fracture surfaces of glassy ceramics which are obtained by sintering glass beads. Such a material mimics the structure of sandstone with the advantage that their porosity may be tuned. They are also found to be self-affine, characterized by a roughness exponent  $\zeta \approx 0.40 \pm 0.04$  significantly lower than the “universal” roughness exponent  $\zeta \approx 0.75$  widely reported in the literature. Its value is found to depend very slightly on the crack growth velocity and the microstructure (grain diameter, porosity) in the range studied. This suggests the existence of a second universality class in failure problems. Its physical origin is then discussed and a model proposed.

Laurent Ponson  
Federal University of Rio de Janeiro

Date submitted: 04 Dec 2006

Electronic form version 1.4