

Abstract Submitted  
for the MAR08 Meeting of  
The American Physical Society

**Influence of dipolar interactions on the formation of domains in layered Ni/Al<sub>2</sub>O<sub>3</sub> nanocomposites** R. DAS, A. HEBARD, University of Florida, A. GUPTA, D. KUMAR, North Carolina Agricultural and Technical State University, S. OH, S. PENNYCOOK, Oak Ridge National Laboratory — Pulsed laser deposition has been used to fabricate Ni/Al<sub>2</sub>O<sub>3</sub> multilayer composites in which Ni nanoparticles of uniform size in the range of 3-60 nm are embedded as layers in an insulating Al<sub>2</sub>O<sub>3</sub> host. At fixed temperatures, the coercive fields show well-defined peaks which define a critical size that delineates a crossover from single domain (SD) to multiple domain (MD) behavior. Most applications require that the particles be single domain with a uniform magnetization that remains stable with a sufficiently large anisotropy energy to overcome thermal fluctuations and beat the superparamagnetic limit, which establishes a temperature-dependent *lower bound* to the particle size (superparamagnetic limit). These considerations must take into account the effect of interactions on magnetic properties as is evident for high-density recording media where particles are very close to each other. The effect of dipolar interactions on the establishment of an *upper bound* to particle size ( $d_c$ ), which defines the crossover from SD to MD behavior will be discussed. We show using coercivity measurements that, with increasing temperature,  $d_c$  increases and then saturates due to attenuated dipolar interactions from thermally induced motions of neighboring randomly oriented particles.

Ritesh Das  
Department of Physics, University of Florida, Gainesville, FL 32611

Date submitted: 14 Dec 2007

Electronic form version 1.4