

Abstract Submitted
for the MAR11 Meeting of
The American Physical Society

T_g depression and segmental dynamics of polystyrene thin films
DANIELE CANGIALOSI, CSIC-CFM, VIRGINIE M. BOUCHER, DIPC, ANGEL ALEGRIA, CSIC-CFM and UPV/EHU, JUAN COLMENERO, CSIC-CFM and DIPC — The glass transition temperature (T_g) of polymer thin films has been a subject of intense debate in the last two decades. (Pseudo)thermodynamic determinations, such as calorimetry and ellipsometry, generally suggest a significant depression of T_g , whereas the dynamic T_g , measured by techniques such broadband dielectric spectroscopy and AC-calorimetry directly probing the molecular mobility, is found to be unchanged. The present study provides a resolution to this controversy on polystyrene by showing that the experimental relaxation time obtained from (pseudo)thermodynamic techniques, and the intrinsic molecular relaxation time can be rescaled on a master curve, only accounting for the thickness of the film. Furthermore the thickness and cooling rate dependence of the (pseudo)thermodynamic T_g is quantitatively captured by the free volume holes diffusion model. In this framework, the T_g depression emerges from the ability of thinner films to maintain equilibrium, due to the shortest distance free volume holes have to diffuse to the polymer interface.

Daniele Cangialosi
CSIC-CFM

Date submitted: 08 Dec 2010

Electronic form version 1.4