

Abstract for an Invited Paper  
for the MAR11 Meeting of  
The American Physical Society

### **Origin of diffuse scattering in relaxor ferroelectrics**

P. GANESH, Center for Nanophase Materials Sciences, Oak Ridge National Laboratory, TN

High-pressure and variable temperature single crystal synchrotron X-ray measurements combined with first-principles based molecular dynamics simulations study diffuse scattering in the relaxor ferroelectric system PSN ( $\text{PbSc}_{1/2}\text{Nb}_{1/2}\text{O}_3$ ). Constant temperature experiments show pressure induced transition to the relaxor phase at different temperatures characterized by butterfly and rod shaped diffuse scattering around the  $\{h00\}$  and  $\{hh0\}$  Bragg spots, respectively. The simulations [1] reproduce the observed diffuse scattering features as well as their pressure-temperature behavior, and show that they arise from polarization correlations between chemically-ordered regions, which in previous simulations were shown to behave as polar nanoregions. Simulations also exhibit radial diffuse scattering (elongated towards and away from  $Q=(000)$ ), that persists even in the paraelectric phase, consistent with previous neutron experiments on ( $\text{PbMg}_{1/3}\text{Nb}_{2/3}\text{O}_3$ ) (PMN). DFPT calculations to elucidate origin of Raman peaks in the relaxor phase will also be presented.

[1] P. Ganesh, E. Cockayne, M. Ahart, R. E. Cohen, B. Burton, Russell J. Hemley, Yang Ren, Wange Yang and Z.-G. Ye, Phys. Rev. B **81**, 144102 (2010)