

Abstract Submitted
for the MAR11 Meeting of
The American Physical Society

**Raman Study of the Verwey Transition in Magnetite (Fe_3O_4)
at High Pressure and Low Temperature: Effect of Aluminum Doping**

Z. SHIRSHIKOVA, L. GASPAROV, Department of Physics, University of North Florida, V. STRUZHUKIN, A. GAVRILIUK, Geophysical Laboratory, Carnegie Institution of Washington, H. BERGER, EPFL, CH-1015 Lausanne, Switzerland — Raman spectra of pure and doped magnetite provide a set of markers allowing one to study how the Verwey transition in magnetite changes with the change of pressure. At ambient pressure Verwey transition temperature, T_v , of the single crystals of magnetite, Fe_3O_4 , is determined to be 123K. High-pressure experiment indicates strong dependence of the change of pressure vs. change in the Verwey transition temperature on the amount of impurities: for pure Fe_3O_4 the change is -0.2 GPa/K; for doped iron, $\text{Fe}_{2.98}\text{Al}_{0.02}\text{O}_4$, the change is -0.09 GPa/K. Aluminum-doped magnetite ($\text{Fe}_{2.98}\text{Al}_{0.02}\text{O}_4$) where Al substitutes Fe^{+2} and Fe^{+3} atoms, represents a 2% aluminum doping, which shifts the Verwey transition temperature to $T_v=118.5\text{K}$. The rate with which the Verwey temperature decreases with pressure is further discussed based on the molar specific heat measurements.

Zhanna A. Shirshikova
University of North Florida

Date submitted: 11 Jan 2011

Electronic form version 1.4