

Abstract Submitted
for the MAR13 Meeting of
The American Physical Society

Oxygen Octahedral Rotations in BaTiO₃/CaTiO₃ Superlattices

MARGARET COSGRIFF, PICE CHEN, NATHANIEL COREY, University of Wisconsin at Madison, XIFAN WU, Temple University, APURVA MEHTA, SLAC National Accelerator Lab, HIROO TAJIRI, Japan Synchrotron Radiation Research Institute, SPring-8, HO NYUNG LEE, Oak Ridge National Laboratory, PAUL EVANS, University of Wisconsin at Madison — Complex oxide superlattices have a wide range of electronic and magnetic properties, which are affected by the structure of the interfaces between different components of the superlattice. The magnitude, coherence, and electric field response of oxygen displacements in three different BaTiO₃/CaTiO₃ superlattice compositions are measured using x-ray diffraction. The displacements are greater in compositions with more consecutive CaTiO₃ layers. The pattern of layer-by-layer alternating displacements is coherent over less than two superlattice unit cells. The net in-phase rotation of the oxygen octahedra gives rise to an x-ray reflection at $(3/2 \ 1/2 \ 1)$. Density functional theory calculations for a $2(\text{BaTiO}_3)/4(\text{CaTiO}_3)$ composition predict a decrease in displacements of oxygen octahedra between barium and calcium layers when an electric field is applied, causing an intensity increase in this reflection. We found the intensity of this reflection for this composition increases by 1.6% when a 12.5 V pulse is applied, a weaker response than the 11% increase predicted. When a 20 V pulse is applied, the reflection intensity actually decreases by 3%, indicating a more complicated response.

Margaret Cosgriff
University of Wisconsin at Madison

Date submitted: 09 Nov 2012

Electronic form version 1.4