

Abstract Submitted
for the MAR16 Meeting of
The American Physical Society

SdH oscillations and pressure effect of the Weyl semimetal NbAs

YONGKANG LUO, Los Alamos National Laboratory, Los Alamos, NM 87545, USA, N. J. GHIMIRE, Argonne National Laboratory, Argonne, Illinois 60439, USA, M. WARTENBE, HONGCHUL CHOI, M. NEUPANE, R. D. MCDONALD, E. D. BAUER, JIANXIN ZHU, J. D. THOMPSON, F. RONNING, Los Alamos National Laboratory, Los Alamos, NM 87545, USA — Via angular Shubnikov-de Hass (SdH) quantum oscillations measurements, we determine the Fermi surface topology of NbAs. The SdH oscillations consist of two frequencies: 20.8 T (α -pocket) and 15.6 T (β -pocket). The analysis shows that the β -pocket has a Berry phase of π and a small effective mass $0.033 m_0$, indicative of a nontrivial topology; whereas the α -pocket has a trivial Berry phase of 0 and a heavier effective mass $0.066 m_0$. Subtle changes can be seen in the $\rho_{xx}(T)$ profiles with pressure up to 2.31 GPa. The Fermi surfaces undergo an anisotropic evolution under pressure, while the topological features of the two pockets remain unchanged. Specific heat measurements reveal a small Sommerfeld coefficient $\gamma_0 = 0.09(1) \text{ mJ}/(\text{mol}\cdot\text{K}^2)$ and a large Debye temperature, $\Theta_D = 450(9) \text{ K}$, confirming a “hard” crystalline lattice. The Kadowaki-Woods ratio and a suppressed transport scattering rate are also studied. **References:** [1] N. J. Ghimire *et al.*, JPCM **27**, 152201 (2015) [2] Y. Luo *et al.*, arXiv: 1506.01751 (2015) [3] Y. Luo *et al.*, arXiv: 1510.08538 (2015)

Yongkang Luo
Los Alamos National Laboratory, Los Alamos, NM 87545, USA

Date submitted: 01 Dec 2015

Electronic form version 1.4