

Abstract Submitted
for the MAR17 Meeting of
The American Physical Society

Low Temperature X-Ray Diffraction Study on CaFe_2As_2

SHUYUAN HUYAN, LIANGZI DENG, ZHENG WU, KUI ZHAO, Department of Physics and TcSUH, University of Houston, Houston, TX 77204- 5005, BING LV, Department of Physics, University of Texas at Dallas, Richardson, TX 75080, YIYU XUE, Department of Physics and TcSUH, University of Houston, Houston, TX 77204- 5005, CHING-WU CHU, Department of Physics and TcSUH, University of Houston, Houston, TX 77204- 5005; Lawrence Berkeley National Laboratory, Berkeley, CA 94720, B. LV COLLABORATION¹, HPLT (PAUL C. W. CHU) TEAM² — For undoped CaFe_2As_2 single crystals, we observed that utilizing thermal treatments could stabilize two pure tetragonal phases PI and PII. Both phases are non-superconducting, while the superconductivity with a T_c up to 25 K can be induced through proper thermal treatment. Room temperature X-ray studies suggest that the origin of superconductivity arises from the interface of the mesoscopically stacked layers of PI and PII. To further investigate, a systematic low temperature X-ray study was conducted over a series of thermal treated CaFe_2As_2 single crystals. From which, we observed the phase aggregation of PI and PII upon cooling, more importantly, an ordered stacking structure exists at low temperature, which closely related to superconducting volume fraction and the ratio of PI and PII. These results further support the proposal of interface-enhanced superconductivity in undoped CaFe_2As_2 . References L. Z. Deng, B. Lv, K. Zhao, F. Y. Wei, Y. Y. Xue, Z. Wu, and C. W. Chu, Phys. Rev. B 93, 054513(2016) K. Zhao, B. Lv, L. Z. Deng, S. Y. Huyan, Y. Y. Xue, and C. W. Chu, Proc. Natl. Acad. Sci. doi: 10.1073/pnas.1616264113

¹UT Dallas

²University of Houston

Shuyuan Huyan
University of Houston

Date submitted: 16 Nov 2016

Electronic form version 1.4