

Abstract Submitted  
for the MAR05 Meeting of  
The American Physical Society

Sorting Category: 16.12.6 (E)

**New Quaternary Hydride  $\text{Li}_3\text{BN}_2\text{H}_8$  with >10 wt% Hydrogen: I. Material Synthesis and Structural Characterization**

GREGORY P. MEISNER, FREDERICK E. PINKERTON, MARTIN S. MEYER, MICHAEL P. BALOGH, General Motors Research and Development Center, MATTHEW KUNDRAT, Aerotek Corp. — We report a new quaternary hydride  $\text{Li}_3\text{BN}_2\text{H}_8$  synthesized from mixed  $\text{LiNH}_2$  and  $\text{LiBH}_4$  powders in a 2:1 molar ratio by ball milling. X-ray diffraction (XRD) results show that as milling time increases, the  $\text{LiNH}_2$  and  $\text{LiBH}_4$  diffraction peaks weaken and a new set of peaks emerges. At 40 min, the sample is substantially converted to the new phase, with only a small remnant of  $\text{LiNH}_2$  in the XRD pattern. After 300 min the conversion is complete, and continued milling up to 960 min produces no further change. The final XRD pattern appears to be single phase, except for a small amount of  $\text{Li}_2\text{O}$  impurity, and has a background intensity that is essentially unchanged with milling time, implying that ball milling does not produce an amorphous phase. All of the observed XRD peaks can be indexed as a single BCC quaternary phase with  $a = 10.76 \text{ \AA}$ . Our *in-situ* XRD data show that  $\text{Li}_3\text{BN}_2\text{H}_8$  forms when mixed  $\text{LiNH}_2$  and  $\text{LiBH}_4$  powders are heated to above  $\sim 95^\circ\text{C}$  without ball milling, then melts at  $\sim 190^\circ\text{C}$ , and finally forms a mixture of solid  $\text{Li}_3\text{BN}_2$  polymorphs upon  $\text{H}_2$  gas release above  $\sim 250^\circ\text{C}$ .

Prefer Oral Session  
 Prefer Poster Session

Gregory P. Meisner  
gregory.p.meisner@gm.com

Date submitted: 01 Dec 2004

Electronic form version 1.4