

Abstract Submitted  
for the MAR08 Meeting of  
The American Physical Society

Sorting Category: 05. (E)

**Quantum Oscillations in the Underdoped Cuprate  $\text{YBa}_2\text{Cu}_4\text{O}_8$** <sup>1</sup> EDWARD YELLAND, University of St Andrews, UK, JOHN SINGLETON, CHUCK MIELKE, NEIL HARRISON, FEDOR BALAKIREV, LANL, BOGDAN DABROWSKI, Northern Illinois University, MARCIN MATUSIAK, JOHN COOPER, University of Cambridge — The quantum oscillations (QOs) seen in the underdoped cuprate superconductor  $\text{YBa}_2\text{Cu}_4\text{O}_8$  (Y124) in magnetic fields up to  $B=85\text{T}$  [1] are strong evidence for a well-defined Fermi surface (FS) in Y124 at low temperature  $T$  and high  $B$ . The QO frequency  $F=660\pm 15\text{T}$ , implies a FS pocket with 2.4% of the full Brillouin zone (BZ) area. Taken with earlier work [2], our data suggest FS pockets are generic to underdoped  $\text{CuO}_2$  planes and give the first hint of doping dependence of the FS. We discuss the carrier concentration implied by the QOs within various models. Comparison of the T-linear specific heat  $\gamma$  (from QO quasiparticle mass  $m^*$ ) to  $\gamma$  estimated from zero-field specific heat measurements constrains the number of FS pockets present in the BZ and supports a reduced BZ due e.g. to a charge/spin density wave or ordered orbital currents. [1] E. A. Yelland et al, arXiv:0707.0057. [2] N. Doiron-Leyraud et al, Nature 446, 565 (2007)

<sup>1</sup>Thanks to EPSRC (U.K.) for financial support. Work supported by DoE grants LDRD-DR-20070085 and BES fieldwork grant, "Science in 100T". Work at NHMFL is performed under the auspices of the National Science Foundation, DoE and the State of Florida

Prefer Oral Session  
 Prefer Poster Session

Edward Yelland  
eay1@st-andrews.ac.uk  
University of St Andrews, UK

Date submitted: 27 Nov 2007

Electronic form version 1.4