

Abstract Submitted
for the MAR06 Meeting of
The American Physical Society

The Magnetic phase diagram of the spin-chain system $\text{Ca}_{2+x}\text{Y}_{2-x}\text{Cu}_5\text{O}_{10-\delta}$: Oxygen hole-doping KEESEONG PARK, Department of Physics, The University of Texas at Austin, JOHN MARKERT, Department of Physics, The University of Texas at Austin — Recently, K. Kudo et al.¹ studied the magnetic ground state in the edge-sharing CuO_2 chains in the spin-chain system $\text{Ca}_{2+x}\text{Y}_{2-x}\text{Cu}_5\text{O}_{10-\delta}$. In that study, the antiferromagnetic transition temperature decreases with increasing x and disappears around $x=1.4$ followed by the appearance of a spin-glass phase at $x=1.5$. We propose that the oxygen content should be included in the hole doping effect by $p = 1/5(x - 2\delta)$ in the spin-chain system. We present x-ray diffraction, magnetic susceptibility, specific heat and iodometric titration measurements² which indicate that an oxygen deficiency shifts the magnetic features toward higher x . For example, for $x = 1$ samples, the single crystals of Ref.1 are equivalent to our oxygen deficient polycrystalline sample with $\delta \approx 0.5$. Such a composition has an only slightly suppressed Néel temperature, while for nearly fully oxygenated $x = 1$ samples, the antiferromagnetic transition is completely suppressed.³

¹K. Kudo, S. Kurogi, and Y.Koike, Physical Review B **71**, 104413 (2005)

²This work is supported by the Robert A. Welch Foundation grant No.F-1191 and the National Science Foundation grant No. DMR-0210383

³M. D. Chabot, and J. T. Markert, Physical Review Letters **86**, 163 (2001)

John Markert
Department of Physics, The University of Texas at Austin

Date submitted: 30 Nov 2005

Electronic form version 1.4