

Abstract Submitted  
for the MAR08 Meeting of  
The American Physical Society

**The 50 K anomaly in the shear modulus of  $\beta$ -PdH<sub>0.71</sub>** DOUGLAS SAFARIK, RICARDO SCHWARZ, Los Alamos National Laboratory — When palladium hydride, PdH<sub>*x*</sub>, is rapidly cooled to liquid helium temperature and then slowly reheated, both the heat capacity and electrical resistivity show a peak in the range  $50 < T < 80$  K, depending on the composition *x*. This “50 K anomaly” has been previously explained in terms of formation of long-range ordered hydrogen superlattice structures. However, several aspects of the 50 K anomaly are inconsistent with an ordering phase transition, namely, the temperature of the anomaly depends on the rate of cooling, and the magnitude of the anomaly is larger for a fast cooling rate than for a slow cooling rate. We have studied the 50 K anomaly by measuring the elastic constants of single-crystal PdH<sub>0.71</sub> in the temperature range  $1.4 < T < 300$  K during both fast cooling and slow warming. During warming, we observed a peak in the shear modulus  $C' = (C_{11} - C_{12}/2)$  at 55 K, which we attribute to the 50 K anomaly. In contrast, we observed no peak in the temperature dependence of the shear modulus  $C_{44}$  or of the bulk modulus  $B$ . We propose that the 50 K anomaly arises not from the formation of long-range ordered hydrogen superlattice structures, but from freezing of the hydrogen short-range order as the hydride is cooled.

Douglas Safarik  
Los Alamos National Laboratory

Date submitted: 05 Dec 2007

Electronic form version 1.4