

MAR09-2008-003197

Abstract for an Invited Paper
for the MAR09 Meeting of
the American Physical Society

Small-Angle Neutron Scattering Studies of Magnetic Correlation Lengths in Nanoparticle Assemblies

SARA MAJETICH, Carnegie Mellon University

Small-angle neutron scattering (SANS) measurements of ordered arrays of surfactant-coated magnetic nanoparticle reveal characteristic length scales associated with interparticle and intraparticle magnetic ordering. The high degree of uniformity in the monodisperse nanoparticle size and spacing leads to a pronounced diffraction peak and allows for a straightforward determination of these length scales [1]. There are notable differences in these length scales depending on the particle moment, which depends on the material (Fe, Co, Fe₃O₄) and diameter, and also on whether the metal particle core is surrounded by an oxide shell. For 8.5 nm particles containing an Fe core and thick Fe₃O₄ shell, evidence of a spin flop phase is seen in the magnetite shell when a field is applied, but not when the shell thickness is ~ 0.5 nm [2]. 8.0 nm particles with an e-Co core and 0.75 nm CoO shell show no exchange bias effects while similar particles with a 2 nm thick shell show significant training effects below 90 K. Polarized SANS studies of 7 nm Fe₃O₄ nanoparticle assemblies show the ability to resolve the magnetization components in 3D.

[1] M. Sachan, C. Bonnoit, S. A. Majetich, Y. Ijiri, P. O. Mensah-Bonsu, J. A. Borchers, and J. J. Rhyne, *Appl. Phys. Lett.* **92**, 152503 (2008).

[2] Yumi Ijiri, Christopher V. Kelly, Julie A. Borchers, James J. Rhyne, Dorothy F. Farrell, Sara A. Majetich, *Appl. Phys. Lett.* **86**, 243102-243104 (2005).

[3] K. L. Krycka, R. Booth, J. A. Borchers, W. C. Chen, C. Conlon, T. Gentile, C. Hogg, Y. Ijiri, M. Laver, B. B. Maranville, S. A. Majetich, J. Rhyne, and S. M. Watson, *Physica B* (submitted).