

Abstract Submitted
for the MAR10 Meeting of
The American Physical Society

High-pressure synthesis and physical properties of the BaIrO₃ polytypes J.-G. CHENG, J.-S. ZHOU, J.B. GOODENOUGH, TMI, University of Texas at Austin, J.A. ALONSO, ICMM, CSIC, Madrid, Spain, E. SUARD, ILL, Grenoble, France, Y. SUI, CCMST, Harbin Institute of Technology, Harbin, China, K. MATSUBAYASHI, Y. UWATOKO, ISSP, University of Tokoyo, Kashiwa, Japan — The ambient 9R-BaIrO₃ exhibits a ferromagnetic transition at $T_c \approx 180$ K followed by a charge density wave at nearly the same temperature.¹ By using the 9R phase as the starting material, we were able to synthesize a series of the polytypes of BaIrO₃, *i.e.* 5H, 6H and 3C phases under high pressure up to 10 GPa at 1000 °C.² These high-pressure phases are quenchable to ambient pressure. The 5H phase has the stacking sequence *hchcc* that is a new member in the hexagonal polytypes of AMO₃ perovskites. With increasing fraction of the corner- to face-sharing IrO_{6/2} octahedra in the sequence 9R→5H→6H, the ground states of BaIrO₃ evolve from a ferromagnetic insulator with $T_c \approx 180$ K in the 9R phase to a ferromagnetic metal with $T_c \approx 50$ K in the 5H phase, and finally to an exchange-enhanced paramagnetic metal near a quantum critical point in the 6H phase.³

¹G. Cao, *et al.*, Solid State Comm. **113**, 657 (2000).

²J.-G. Cheng, *et al.*, J. Am. Chem. Soc. **131**, 7461 (2009).

³J.-G. Cheng, *et al.*, Phys. Rev. B **80**, 104430 (2009).

Jinguang Cheng
TMI, University of Texas at Austin

Date submitted: 12 Nov 2009

Electronic form version 1.4