

Abstract Submitted  
for the MAR10 Meeting of  
The American Physical Society

**Cohesive Strength of Metal/Ceramic Interfaces Fe/ $M$ [C,N] and the Role of Misfit Dislocations and Interface Roughness<sup>1</sup>**

OLEG Y. KONTSEVOI, A.J. FREEMAN, G.B. OLSON, Northwestern University — The dispersed inclusions of carbides and nitrides were shown to provide superior fracture toughness and increased strength for steels. To obtain a fundamental understanding of their effect, we investigated the theoretical cohesive strength of Fe/ $M$ [C,N] ( $M$ =Ti,V,Nb,Mo) interfaces using the first principles calculations with the full-potential linearized augmented plane wave (FLAPW) method. For the coherent  $\langle 100 \rangle \{ 001 \} \text{Fe} // \langle 110 \rangle \{ 001 \} MC$  interfaces, the highest theoretical strength of 3.78 J/m<sup>2</sup> was obtained for the Fe/VC interface, and it decreases from V-Ti-Nb-Mo. The strength of nitride interfaces is 10-15% lower than for carbides. Within the Peierls-Nabarro model with *ab initio* generalized stacking fault energetics, we estimated that the misfit dislocations which may form due to lattice misfit decrease the interface strength by 20%. The strength of  $\langle 110 \rangle \{ 110 \} \text{Fe} // \langle 010 \rangle \{ 100 \} \text{TiC}$  semicoherent interfaces that contain primary misfit dislocations was found to be 30% lower. The effect of interface steps and roughness on strength is also investigated. We further identify the origins of strong interfacial bonding based on electronic structure and charge densities analyzes.

<sup>1</sup>Supported by the ONR through D3D Consortium

Oleg Y. Kontsevoi  
Northwestern University

Date submitted: 20 Nov 2009

Electronic form version 1.4