

Abstract Submitted  
for the MAR11 Meeting of  
The American Physical Society

**High frequency conductivity of few unit cell thick  $\text{LaNiO}_3$  layers<sup>1</sup>**

DANIEL OUELLETTE, Department of Physics, University of CA, Santa Barbara, JUNWOO SON, SUSANNE STEMMER, Materials Department, University of CA, Santa Barbara, S. JAMES ALLEN, Department of Physics, University of CA, Santa Barbara — We have measured the dc and optical conductivity of ultra-thin films of the correlated metal  $\text{LaNiO}_3$  and of superlattices with alternating  $\text{LaNiO}_3$  and insulating  $\text{SrTiO}_3$  layers, all grown epitaxially on LSAT substrates with modest tensile strain in the  $\text{LaNiO}_3$ . In the superlattices, the  $\text{LaNiO}_3$  layers are 4 unit cells (1.6 nm) thick and the  $\text{SrTiO}_3$  is either 4 or 10 unit cells thick. Isolated films thinner than 4 nm are insulating; however, both the superlattices and thicker films consistently show a coherent peak in the optical conductivity. Furthermore, the optical conductivity at several hundred GHz is in excellent agreement with the dc electrical conductivity. We consider the possibility of a percolation threshold in ultra-thin  $\text{LaNiO}_3$  layers and discuss implications for the nature of the  $\text{LaNiO}_3/\text{SrTiO}_3$  interface.

<sup>1</sup>Support from the Army Research Office through a MURI program is gratefully acknowledged.

Daniel Ouellette  
Department of Physics, University of CA, Santa Barbara

Date submitted: 19 Nov 2010

Electronic form version 1.4