

Abstract Submitted  
for the MAR14 Meeting of  
The American Physical Society

**Plasmonic Resonant Absorption in Mid-Infrared in Graphene**

**Nanoresonators** DON C. ABEYSINGHE, Air Force Research Lab, Materials and Manufacturing Directorate, AFRL/RXAN, JOSHUA MYERS, Wright State University, NIMA N. ESFAHANI, Air Force Research Lab, Sensors Directorate, AFRL/RYDH, DENNIS E. WALKER JR., Air Force Research Lab, Sensors Directorate, AFRL/Rydd, JOSHUA R. HENDRICKSON, JUSTIN CLEARY, Air Force Research Lab, Sensors Directorate, AFRL/RYDH, SHIN MOU, Air Force Research Lab, Materials and Manufacturing Directorate, AFRL/RXAN, AIR FORCE RESEARCH LABORATORY, MATERIALS & MANUFACTURING DIRECTORATE, WRIGHT-PATTERSON AFB, OH, USA TEAM, AIR FORCE RESEARCH LABORATORY, SENSORS DIRECTORATE, WRIGHT-PATTERSON AFB, OH, USA TEAM — We experimentally demonstrated polarization-sensitive, tunable plasmonic resonant absorption in the mid-infrared range of 5-14  $\mu\text{m}$  by utilizing an array of graphene nanoribbon resonators. By tuning resonator width and charge density, we probed graphene plasmons with  $\lambda_p \leq \lambda/100$  and plasmon resonance energy as high as 0.26 meV ( $2100 \text{ cm}^{-1}$ ) for 40 nm wide nanoresonators. Resonant absorption spectra enabled us to map the wavevector-frequency dispersion for graphene plasmons at mid-IR energies and revealed a modified plasmon dispersion as well as plasmon damping due to intrinsic optical phonons of graphene and graphene plasmon interaction with the surface polar phonons in  $\text{SiO}_2$  substrates. Additionally, we studied spectra further by introducing intrinsic defect phonons and doping by direct electron beam irradiation of graphene nanoresonators

Don Abeyasinghe  
Air Force Research Lab, Materials and Manufacturing Directorate

Date submitted: 14 Nov 2013

Electronic form version 1.4