

Abstract Submitted  
for the SHOCK09 Meeting of  
The American Physical Society

**Elastic Wave Amplitude and Attenuation in Shocked Pure AL**

J.M. WINEY, P.B. TRIVEDI, B.M. LALONE, Y.M. GUPTA, Wash. State Univ., R.F. SMITH, J.H. EGGERT, G.W. COLLINS, Lawrence-Livermore Nat. Lab. — Shock-induced elastic-plastic deformation in pure aluminum was examined at 4 GPa peak stress by measuring wave profiles in thin (40–180  $\mu\text{m}$ ) samples under plate impact loading. Large elastic wave amplitudes ( $\sim 1$  GPa) and rapid elastic wave attenuation with propagation distance were observed, indicating a time-dependent elastic-plastic response. These results are in contrast to the  $\sim 0.1$  GPa elastic wave amplitudes observed in past work (*J. Appl. Phys.* **98**, 033524 (2005)) using thick ( $>1$  mm) samples. The combination of large elastic wave attenuation in thin samples and differences in sample thicknesses between the present and past work suggests a consistent picture of shock wave propagation in pure aluminum: manifestations of time-dependent elastic-plastic response are confined to material very near the impact surface. The present results cannot be fully reconciled with recent shockless compression results (*Phys. Rev. Lett.* **98**, 065701 (2007)). Work supported by DOE.

Michael Winey  
Washington State University

Date submitted: 18 Feb 2009

Electronic form version 1.4